

Intertek ETL Semko
FMVSS 302
Test Results

(This is not a test report)

CLIENT: Crane Composites
PROJECT NUMBER: 3129875SAT-002
DATE: 8/21/2007
SPECIMEN I.D.: J1653-239
FRP Panels - RBP 045 - Filon G-III

Test Criteria

The burning rate must not be more than 102 mm per minute. If a material stops burning before it has burned for 60 seconds from the start of timing, and has not burned more than 51 mm from the point where timing started, it is considered passing.

| Specimen | Total Time (sec) | Extent of Burning (mm) | Burning Rate (mm/min) |
|-----------------|-------------------------|-------------------------------|------------------------------|
| 1 | 434 | 254 | 35.1 |
| 2 | 425 | 254 | 35.9 |
| 3 | 461 | 254 | 33.1 |

THIS TEST SPECIMEN PASSED THE FMVSS 302 FIRE TEST.