



SGS U.S. Testing Company Inc.

291 Fairfield Avenue
Fairfield, NJ 07004
Tel: 201-575-5252
Fax: 201 575-0799

REPORT NUMBER: 511638
DATE: 12/17/96
PAGE: 1 OF 2

CLIENT: Crane Kemlite Company, Inc.
23525 W. Eames Street
Channahon, IL 60410

Attn: Molly Dickerman

AUTHORIZATION: Letter of authorization received from Molly Dickerman of Crane Kemlite Co., Inc., dated 11/26/96.

SAMPLE ID: Two (2) sets of samples received from the client on 12/4/96. Client identified the samples as:
"K961127-1 & 2, 2585 RISC - MD & XMD"
"K961127-3 & 4, 2508 TIW - MD & XMD"

TEST PROCEDURE: Selected test as listed on the following page.

TEST DATES: 12/10 - 12/13/96

RESULTS: Continued on Page 2.

PREPARED BY:

Linda Kinderman
Technician - Flammability
Textile Services

vac

SIGNED FOR COMPANY BY:

Howard Barbara
Department Manager - Flammability
Textile Services

Member of the SGS Group

ANALYTICAL SERVICES • PERFORMANCE TESTING • STANDARDS EVALUATION • CERTIFICATION SERVICES
SGS U.S. TESTING COMPANY INC. REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANYONE RELYING ON SUCH REPORTS SHOULD UNDERSTAND ALL OF THE DETAILS OF THE ENGAGEMENT. REPORTS REFLECT RESULTS ONLY OF THE STANDARDS OR PROCEDURES IDENTIFIED TO THE TESTS CONDUCTED AND ARE LIMITED TO THE SAMPLES TESTED. TEST RESULTS MAY NOT BE INDICATIVE OF THE QUALITIES OF THE LOT FROM WHICH THE SAMPLE WAS TAKEN. SGS U.S. TESTING COMPANY INC. HAS NOT CONDUCTED ANY QUALITY CONTROL PROGRAM FOR THE CLIENT. NEITHER THE NAME, SEALS, MARKS NOR INSIGNIA OF SGS U.S. TESTING COMPANY INC. MAY BE USED IN ANY ADVERTISING OR PROMOTIONAL MATERIALS WITHOUT THE PRIOR WRITTEN APPROVAL OF SGS U.S. TESTING COMPANY INC. THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL WITHOUT THE WRITTEN PERMISSION OF THE SGS U.S. TESTING COMPANY INC. SAMPLES NOT DESTROYED IN TESTING ARE DISPOSED OF AFTER 30 DAYS.

REPORT OF TEST

REPORT NUMBER: 511638

DATE: 12/17/96

PAGE: 2 OF 2

CLIENT: Crane Kemlite

RESULTS:

Flammability

FMVSS-302

Department of Transportation Motor Vehicle Safety Standard 302 Flammability of Interior Materials as published in the Federal Register Rev. 10-1-92.

	Burn Time*		Burn Distance		Burn Rate	
	(seconds)		(inches)		(in./min.)	
	<u>MD</u>	<u>XMD</u>	<u>MD</u>	<u>XMD</u>	<u>MD</u>	<u>XMD</u>
K961127	300.0	300.0	5.2	4.8	1.0	1.0
1 & 2	300.0	300.0	4.9	5.0	1.0	1.0
2585 RISC	300.0	300.0	4.8	4.9	1.0	1.0
K961127	300.0	300.0	4.8	4.3	1.0	0.9
3 & 4	300.0	300.0	4.9	4.0	1.0	0.8
2508 TIW	300.0	300.0	5.3	5.1	1.1	1.0

*Tests were discontinued after 5 minutes.

Requirements: The material shall not burn or transmit a flame front across its surface, at a rate of more than 4 inches per minute. However, if a material stops burning before it has burned for 60 seconds from the start of timing and has not burned more than 2 inches from the point where timing was started, it shall be considered to meet this requirement.

Conclusion: The submitted samples were found to meet the requirements of the above standard.

End of Report