

## Composites

## KEMLITE® high strength liner

## EMBOSSED WITH RANDOM CHOPPED FIBERGLASS

## **PRODUCT**

Kemlite high strength liner, LHS, is a lightweight and durable fiberglass reinforced plastic (frp) panel. It is more cleanable, more stain resistant, and more abrasionresistant than competitive frp panels. Kemlite is comprised of random chopped fiberglass and polyester resin.

## **PURPOSE**

Kemlite high strength liner, LHS, is specifically designed and formulated for refrigerated and dry  $\,$ 

van trailers.



PRODUCT CODE: LHS

### **DESIGN PROPERTIES**

PRODUCT CODE	NOMINAL THICKNESS	NOMINAL WEIGHT	FINISH	MAXIMUM LENGTH	MINIMUM WIDTH	MAXIMUM WIDTH	COLOR
LHS	0.06" 1.5 mm	0.35 lbs/ft² 1.71 kg/m2	Embossed	Available up to 800'   243.8 m	11"   0.3 m	106"   2.7 m	White   85

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	LHS	TEST METHOD	
FLEXURAL STRENGTH	27 x 10³ psi   186 MPa	ASTM - D790	
FLEXURAL MODULUS	0.8 x 10° psi   5516 Mpa	ASTM - D790	
TENSILE STRENGTH	14 x 10³ psi   97 MPa	ASTM - D638	
TENSILE MODULUS	1.2 x 10º psi   8274 MPa	ASTM - D638	
BARCOL HARDNESS	40	ASTM - D2583	
COEFFICIENT OF LINEAR THERMAL EXPANSION	1.3 x 10 <sup>-5</sup> 10/10/°F   23 µm/m/°C	ASTM - D696	
THERMAL CONDUCTIVITY	0.4 Btu∙in/hr∙ft² ºf   5.0 cal∙cm/hr∙m² ºC	ASTM - C177	
WATER ABSORPTION	0.3%/24hrs @77°F   25°C	ASTM - D570	
SPECIFIC GRAVITY	1.57	ASTM - D792	
GARDNER IMPACT STRENGTH	50 in-lb   5.6 J	ASTM - D5420	
PUNCTURE STRENGTH	150 lb   68 kg	internal	

#### **SPECIFICATIONS**

Crane Composites, Inc. (CCI) panels are manufactured in lengths and widths as required.

#### **COMPOSITION**

Reinforcement: Random chopped fiberglass.

Resin Mix: Modified polyester copolymer, inorganic fillers, and pigments

#### FINISHED PANEL QUALITY

- 1. The frontside of the panel shall have a pebble-like embossed finish. The backside of the panel shall have a smooth finish. The backside surface may have some variations which do not affect functional properties and are not cause for rejection. The backside of the panel is comprised of a polyester copolymer surface that is commonly bonded with adhesives or to foam in lamination processes. Typically, no additional preparation is required as long as the surface is dirt and oil free.
- 2. Physical properties shall be as set forth on Page 1.
- Dimensions shall be as specified on purchase order, subject to the following tolerances:

WIDTH:  $\pm 1/8"$  ( $\pm 3.2 \text{ mm}$ )

LENGTH: ±1/8" (±3.2 mm) up to 12' (3.7 m)
SQUARENESS: ±1/8" (3.2 mm) in 48" (1.2 m) of width

4. Average thickness: For thickness  $\leq 0.100$ ",  $\pm 0.010$ "

For thickness > 0.100",  $\pm 10\%$ 

5. Bulk Coil policy #6207 applies

#### **CERTIFICATIONS**

- 1. Meets USDA/FSIS requirements. Reference document #6776 for conformance statement.
- 2. Meets FMVSS 302 requirements

#### **IDENTIFICATION**

Product identified by 2 green threads on back

#### DESIGN DATA NOTES

 Bulk coil may be ordered in long lengths or in specific cutto-size pieces. Standard coil lengths are 250' and 500', custom sizes are available. Crane Composites reserves the right to manufacture and ship total linear footage of long length bulk coils ordered within the following parameter lengths per piece:

Min. 250' | 61.0 m Max. 800' | 243.8 m

Cut-to-size lengths 12' (3.7 m) and over of the same width will be interlapped (18"-36" [457.2 mm-914.4 mm] interlap per panel) into a coil for ease of handling and shipping.
 Total length tolerance – 0" and +6" (-0 mm and +152.4 mm).

#### STAINING STATEMENT

Some staining/discoloration may occur to frp liner panels after they have been in service for several years. This is a normal wear condition. As long as acceptable cleaning methods (i.e., steam cleaning) are used, the surface should remain sanitary and acceptable.

#### FABRICATING RECOMMENDATIONS

NOTE: Protect your eyes with goggles; cover your nose and mouth with a filter mask; cover exposed skin when cutting CCl panels. HAND FABRICATING: Drilling—High speed drill bit (60° cutting angle, with 12°-15° clearance) or hole saw.

STAPLING: Standard pneumatic stapler.

CUTTING: Sheet metal shears or circular saw with reinforced carborundum or carbide-tipped blade.

PRODUCTION FABRICATING: Use carbide-tipped tools. Straight cuts can be sheared (90° cutting edge with 0.002" [0.05 mm] clearance) or sawed. For irregular cuts, use die punch or band saw. PAINTING PREPARATION: You should always test and validate the selected paint system with the frp panel prior to application. To properly prepare the panel surface for painting, make sure the surface is clean, dry, and free from all oils, grease, silicones, dust, and other contaminants. Common practices for preparation before painting include using alkaline detergents or clean water. Sanding or roughening of the panel surface is recommended to promote paint adhesion. 600 grit or finer sand paper or a 3M "Ultrafine" Scotch-Brite® pad are commonly used to roughen the surface. CLEANING INSTRUCTIONS: Contact us for cleaning instructions. SDS: Prior to working with our products, see our most current SDS at cranecomposites.com/sds.html.

### STORAGE REQUIREMENTS

Crane Composites panels are designed for peak performance prior to and after the panels have been applied. Careful handling during the manufacturing process is important. Avoid excessive clamping, dropping and scraping. Keep contents dry. Store indoors in a well ventilated area. When outside storage is necessary, cover and protect from the weather and exposure to sunlight.

# PLEASE NOTE THE FOLLOWING PRODUCT USE INFORMATION:

Products manufactured by CCI will provide a clean, aesthetically pleasing finished installation. However, by nature, fiberglass reinforced plastic panels may occasionally have small areas that are aesthetically unacceptable for use. Panels should be inspected onsite prior to installation or lamination and original CCI skid tag/ticket number removed and retained. If any portion of material will not provide an acceptable appearance, CCI should be notified at once. Please report the non-conforming product utilizing the retained skid tag/ticket number. Upon verification of unacceptability, CCI will replace or refund the purchase price of the non-conforming product.

We believe all information given is accurate, without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents. www.astm.org/Standards/E84.htm.

A global leading provider of resilient wall and ceiling coverings. Kemlite® was established in 1954 and the company changed names to Crane Composites in 2007. Crane Composites is headquartered in Channahon, IL and all our products are easily accessible and readily available to our customers.

The following are trademarks of Crane Composites, Inc. or a related company: ArmorTuf, Kemlite, Reefer Roof, SunPatch, and Surfaseal

